

2

new dimension

C

performance/testing

BEST

DESCRIPTION/TEST METHOD	STANDARD REQUIREMENT	BEST: TEST RESULTS
Dimensional Deviations AS/NZS 4456.3	+/- 2mm	+/- 1.5mm
Characteristic Breaking Load (kN) AS/NZS 4456.5	> 5.0 (Pedestrian only) > 7.0 (Pedestrian & Light Vehicle)	6.0 (40mm) 10.78 (60mm)
Abrasion Resistance (mean abrasion index) AS/NZS 4456.9	< 7.0 (low volume) < 5.0 (medium volume) < 3.5 (high volume)	3
Slip Resistance (co-efficient of friction) AS/NZS 3661.1	> 0.4	0.76
Salt Resistance (cycles) AS/NZS 4456.10	> 40 Cycles	No deterioration after 40 cycles

N.B.: Performance results are typical BEST values. BEST will on request, generate specific product test results.

