Technical Specifications
New Generation Terrazzo Tile Range (Page 1 of 2)

Best Bricks & Pavers

Resistance to Salt Attack AS/NZS 4456.10B	Protected	General Purpose		Exposure
				✓
	Only suitable for use in locations protected from external weathering	Resistant to decay in non-saline environments (e.g. normal external paving)		Resistant to decay in saline environments (e.g. pool surrounds)

Dimensional Deviation AS/NZS 4456.3B	DP0	DPB1	DPB2	DPB3	DPB4
					✓
	No Requirement	Plan: +/- 3.0 Std Deviation: 2.0 Height: +/- 2.5 Std Deviation: 3.0	Plan: +/- 2.5 Std Deviation: 2.0 Height: +/- 2.0 Std Deviation: 3.0	Values as agreed between supplier and purchaser.	Plan: +/- 2.0 Std Deviation: 1.5 Height: +/- 2.0 Std Deviation: 2.0

Breaking Load of Segmental Pavers AS/NZS 4456.5	Residential			Public Space			Trafficked
	Pedestrian	Light Vehicle	Commercial	Pedestrian	Light Vehicle	Commercial	
300 x 300 x 40mm	✓			✓			
400 x 400 x 40mm	✓			✓			
300 x 300 x 50mm	✓	✓		✓	✓		
600 x 300 x 50mm	✓			✓			
300 x 200 x 60mm	✓	✓	✓	✓	✓	✓	✓
300 x 300 x 60mm	✓	✓	✓	✓	✓	✓	✓
400 x 400 x 60mm	✓	✓		✓	✓		
600 x 400 x 60mm	✓	✓		✓	✓		
	A pavement only subjected to foot traffic	A vehicle with gross weight of less than 3 ton.	A vehicle with gross weight of more than 3 ton.	A pavement only subjected to foot traffic	A vehicle with gross weight of less than 3 ton.	A vehicle with gross weight of more than 3 ton.	Vehicles per day: Minor: <400 Local: 400-1000 Collector: 1000-2000

	Surface Finish	P0 & P1	P2	P3	P4	P5
Slip Resistance AS 4586:13	Honed	✓	✓	✓	✓	
	Black Series	✓	✓	✓	✓	✓
	Sawn	✓	✓	✓	✓	✓
		Internal dry areas only	Internal areas subjected to occasional water tracking	Undercover carparks Undercover concourses Dry stair treads	External walkways Wet stair treads Swimming pool surrounds	External ramps Loading docks Swimming pool ramps

	Surface Finish	Test	
Skid Resistance as per DPTI Test Procedure TN024 01/2016 based on 5000 wear cycles	Honed		(300x300x60mm 300x200x60mm Thickness only)
	Black Series	✓	